

**TYPICAL PROPERTIES OF THE OXIDIZED POLYETHYLENE WAX****Marcus “ MC – 629LM ”**

Properties	Specification
Melting Point (ASTM D 3418), Deg.C	70 ± 5
Drop Melting Point (ASTM D 3954), Deg.C	80 ± 5
Penetration (ASTM D 1321) dmm @ 5 Secs at 23 Deg.C	4 - 8
Viscosity (ASTM D 3236), cps @ 149 Deg.C	15 ± 5
Density (ASTM C 693), Gms/cc	0.93 ~ 0.94
Acid No. (ASTM D 1386) mgms KOH/gm	16 ± 1
Color - Hunter Lab. (ASTM E-313)	White
Form	Prill

CAS Number: 68441 – 17 - 8**For Marcus Oils & Chemicals Pvt. Ltd.****Chittaranjan Maity**